

Technical Data

Magnetic Properties		
Coercivity (Hc)		127.3 kA/m
Retentivity (Br)		265 mT
Physical Properties		
Thickness	Magnetic Layer	3.1 μm
	Total	13.5 μm
Tape Width		12.65 mm
Yield Strength		27 N
Breaking Tensile Strength		39 N
Residual Elongation		Less than 0.18 %
Performance		
Video RF Output		0 dB*
Video C/N		0 dB*
Audio Sensitivity		0 dB*
Audio Frequency Response		0 dB*

Note

Figures are typical values of 33M tape based on Fujifilm's standard measurement procedures.

The Figures marked with * are comparisons with the Fujifilm reference tape.