

## Technical Data

Magnetic Properties	
Coercivity (Hc)	131 kA/m
Retentivity (Br)	270 mT
Physical Properties	
Tape Thickness: Total	14 $\mu$ m
Tape Width	12.65 mm
Yield Strength	25 N
Breaking Tensile Strength	40 N
Residual Elongation	0.04%
Performance	
Video RF Output	0 dB*
Video C/N	0 dB*
Audio Sensitivity	0 dB*
Audio Frequency Response	0 dB*

### Note

Figures are typical values based on Fujifilm's standard measurement procedures.  
The figures marked with \* are comparisons with the Fujifilm Digital Betacam reference tape.